KPS "L", SnPb Termination, X7R Dielectric, 10 – 250 **VDC (Commercial Grade)**



Overview

KEMET Power Solutions (KPS) Commercial "L" with Tin/ Lead Termination stacked capacitors utilize a proprietary lead-frame technology to vertically stack one or two multilayer ceramic chip capacitors into a single compact surface mount package. The attached lead-frame mechanically isolates the capacitor's from the printed circuit board, therefore offering advanced mechanical and thermal stress performance. Isolation also addresses concerns for audible, microphonic noise that may occur when a bias voltage is applied. A two chip stack offers up to double the capacitance in the same or smaller design footprint when compared to traditional surface mount MLCC devices. Providing up to 10 mm of board flex capability, KEMET's tin/lead electroplating process is designed to meet a 5% minimum lead content and address concerns for a more robust and reliable lead containing

termination system. As the bulk of the electronics industry moves towards RoHS compliance, KEMET continues to provide tin/lead terminated products for military, aerospace and industrial applications and will ensure customers have a stable and long-term source of supply. These devices provide lower ESR, ESL and higher ripple current capability when compared to other dielectric solutions.

Combined with the stability of an X7R dielectric, KEMET's KPS devices exhibit a predictable change in capacitance with respect to time and voltage and boast a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to ±15% from -55°C to +125°C.

Benefits

- Operating temperature range of -55°C to +125°C
- Reliable and robust termination system
- EIA 1210 and 2220 case sizes
- DC voltage ratings of 10 V, 16 V, 25 V, 50 V, 100 V and 250 V
- Capacitance offerings ranging from 0.1 up to 47 μF



Ordering Information

C	2220	C	106	M	5	R	2	L	7186
Ceramic	Case Size (L" x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance ¹	Rated Voltage (VDC)	Dielectric	Failure Rate/ Design	Leadframe Finish ²	Packaging/ Grade (C-Spec)
	1210 2220	C = Standard	Two Significant Digits and Number of Zeroes	K = ±10% M = ±20%	8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 A = 250	R = X7R	1 = KPS Single Chip Stack 2 = KPS Double Chip Stack	L = SnPb (5% Pb min.)	See "Packaging C-Spec Ordering Options Table" below

¹ Double chip stacks ("2" in the 13th character position of the ordering code) are only available in M (\pm 20%) capacitance tolerance. Single chip stacks ("1" in the 13th character position of the ordering code) are available in K (\pm 10%) or M (\pm 20%) tolerances.

² Additional leadframe finish options may be available. Contact KEMET for details.



Packaging C-Spec Ordering Options Table

Packaging Type ¹	Packaging/Grade Ordering Code (C-Spec)			
7" Reel (Embossed Plastic Tape)/Unmarked	7186			
13" Reel (Embossed Plastic Tape)/Unmarked	7289			

¹ The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. The option to laser mark is not available on these devices. For more information see "Capacitor Marking."

Benefits cont'd

- Available capacitance tolerances of ±10% and ±20%
- Higher capacitance in the same footprint
- · Potential board space savings
- · Advanced protection against thermal and mechanical stress
- · Provides up to 10mm of board flex capability
- Reduces audible, microphonic noise
- Extremely low ESR and ESL
- SnPb plated termination finish (5% Pb minimum)
- · Non-polar device, minimizing installation concerns
- · Tantalum and electrolytic alternative

Applications

Typical applications include smoothing circuits, DC/DC converters, power supplies (input/output filters), noise reduction (piezoelectric/mechanical), circuits with a direct battery or power source connection, critical and safety relevant circuits without (integrated) current limitation, and any application that is subject to high levels of board flexure or temperature cycling. Markets include industrial, aerospace, automotive and telecommunications.




Qualification/Certification

Commercial grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.

Environmental Compliance

These devices do not meet RoHS criteria due to the concentration of Lead (Pb) in the termination finish.

Dimensions - Inches (Millimeters)



Number of Chips	EIA SIZE CODE	METRIC SIZE CODE	L LENGTH	W WIDTH	H HEIGHT	LW LEAD WIDTH	Mounting Technique
Cingle	1210	3225	3.50 (0.138) ±0.30 (0.012)	2.60 (0.102) ±0.30 (0.012)	3.35 (0.132) ±0.10 (0.004)	0.80 (0.032) ±0.15 (0.006)	
Single	2220	5650	6.00 (0.236) ±0.50 (0.020)	5.00 (0.197) ±0.50 (0.020)	3.50 (0.138) ±0.30 (0.012)	1.60 (0.063) ±0.30 (0.012)	Solder Reflow
Double	1210	3225	3.50 (0.138) ±0.30 (0.012)	2.60 (0.102) ±0.30 (0.012)	6.15 (0.242) ±0.15 (0.006)	0.80 (0.031) ±0.15 (0.006)	Only
	2220	5650	6.00 (0.236) ±0.50 (0.020)	5.00 (0.197) ±0.50 (0.020)	5.00 (0.197) ±0.50 (0.020)	1.60 (0.063) ±0.30 (0.012)	



Electrical Parameters/Characteristics

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 Vdc Applied (TCC)	±15%
¹ Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
² Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5 ±1 seconds and charge/discharge not exceeding 50 mA)
³ Dissipation Factor (DF) Maximum Limit at 25°C	5% (10 V), 3.5% (16 V and 25 V) and 2.5%(50 V to 250 V)
⁴ Insulation Resistance (IR) Minimum Limit at 25°C	See Insulation Resistance Limit Table (Rated voltage applied for 120 ±5 seconds at 25°C)

¹ Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 48 or 1,000 hours. Please refer to a part number specific datasheet for referee time details.

1 kHz ± 50 Hz and 1.0 ± 0.2 V_{rms} if capacitance $\leq 10 \mu F$

120 Hz ±10 Hz and 0.5 ±0.1 V_{rms} if capacitance > 10 μF

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

Post Environmental Limits

High Temperature Life, Biased Humidity, Moisture Resistance										
Dielectric	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance					
	> 25		3.0							
X7R	16/25	All	5.0	±20%	10% of Initial Limit					
	< 16		7.5							

Insulation Resistance Limit Table

EIA Case Size	1,000 Megohm Microfarads or 100 GΩ	500 Megohm Microfarads or 10 GΩ
1210	< 0.39 µF	≥ 0.39 µF
2220	< 10 µF	≥ 10 µF

² DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.


³ Capacitance and dissipation factor (DF) measured under the following conditions:

⁴ To obtain IR limit, divide M Ω - μ F value by the capacitance and compare to G Ω limit. Select the lower of the two limits.




Electrical Characteristics


Z and ESR C1210C475M5R1L




Z and ESR C2220C476M3R2L




Impedance - 1210, .22 μF, 50 V X7R



Z and ESR C2220C225MAR2L




ESR - 1210, .22 μF, 50 V X7R






Electrical Characteristics cont'd

Microphonics - 1210, 4.7 μF, 50 V, X7R




Microphonics - 2220, 47 μF, 25 V, X7R




Competitive Comparision


Microphonics - 1210, 4.7 μF, 50 V, X7R




Microphonics - 2220, 22 μF, 50 V, X7R



Microphonics – 1210, 22 μ F, 25 V, X7R



Ripple Current (Arms) 2220, 22 µF, 50 V




Note: Refer to Table 4 for test method.




Electrical Characteristics cont'd

Board Flex vs. Termination Type



Board Flex vs. Termination Type



Board Flexure to 10 mm






Table 1A - Capacitance Range/Selection Waterfall (1210 & 2220 Case Sizes)

	Case Size/Series			C1210C					C2220C					
	Capacitance	Voltag	e Code	8	4	3	5	1	Α	4	3	5	1	A
Capacitance	Code	Rated Volt	age (VDC)	10	16	25	50	100	250	16	25	50	100	250
		Capacitance Tolerance		Draduat Availability and Chin Thickness Codes										
	Single Chip Stack													
0.10 μF	104	K	М	FV	FV	FV	FV	FV	FV	JP	JP	JP	JP	JP
0.22 μF	224	К	M	FV	FV	FV	FV	FV		JP	JP	JP	JP	JP
0.47 µF	474	К	М	FV	FV	FV	FV	FV		JP	JP	JP	JP	JP
1.0 μF	105	К	М	FV	FV	FV	FV	FV		JP	JP	JP	JP	JP
2.2 μF	225	К	М	FV	FV	FV	FV			JP	JP	JP	JP	
3.3 µF	335	К	М	FV	FV	FV	FV			JP	JP	JP	JP	
4.7 μF	475	К	М	FV	FV	FV	FV			JP	JP	JP		
10 μF	106	К	М	FV	FV	FV				JP	JP	JP		
15 μF	156	К	М	FV						JP	JP			
22 μF	226	К	М	FV						JP	JP			
33 μF	336	К	М											
47 μF	476	К	М											
100 µF	107	lκ	М											
				Do	uble C	hip Sta	ıck							
0.10 μF	104		М	FW	FW	FW	FW	FW	FW	JR	JR	JR	JR	JR
0.22 µF	224		М	FW	FW	FW	FW	FW	FW	JR	JR	JR	JR	JR
0.47 μF	474		м	FW	FW	FW	FW	FW		JR	JR	JR	JR	JR
1.0 µF	105		м	FW	FW	FW	FW	FW		JR	JR	JR	JR	JR
2.2 μF	225		м	FW	FW	FW	FW	FW		JR	JR	JR	JR	JR
3.3 µF	335		м	FW	FW	FW	FW	FW		JR	JR	JR	JR	
4.7 μF	475		М	FW	FW	FW	FW			JR	JR	JR	JR	
10 μF	106		M	FW	FW	FW	FW			JR	JR	JR		
22 μF	226		M	FW	FW	FW				JR	JR	JR		
33 μF	336		M	FW						JR	JR			
47 μF	476		M	FW						JR	JR			
100 μF	107		M											
220 µF	227		M											
		Rated Vol		10	16	25	50	100	250	16	25	50	100	250
Capacitance	Capacitance		e Code	8	4	3	5	1	Α	4	3	5	1	A
Capacitance	Code	Case Siz	e/Series		C1210C					'	C22200			

Table 2 – Chip Thickness/Tape & Reel Packaging Quantities


Thickness	Case	Thickness ±	Paper C	Quantity	Plastic Quantity		
Code	Size	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel	
FV	1210	3.35 ±0.10	0	0	600	2,000	
FW	1210	6.15 ±0.15	0	0	300	1,000	
JP	2220	3.50 ±0.30	0	0	300	1,300	
JR	2220	5.00 ±0.50	0	0	200	800	
Thickness	Case	Thickness ±	7" Reel	13" Reel	7" Reel	13" Reel	
Code	Size	Range (mm)	Paper (Quantity	Plastic (Quantity	

Package quantity based on finished chip thickness specifications.



Table 3 – KPS Land Pattern Design Recommendations (mm)

EIA SIZE CODE	METRIC SIZE	Median (Nominal) Land Protrusion							
CODE	CODE	С	Y	X	V 1	V2			
1210	3225	1.50	1.14	1.75	5.05	3.40			
2220	5650	2.69	2.08	4.78	7.70	6.00			



Soldering Process


KEMET's KPS devices are compatible with IR reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for IR reflow reflect the profile conditions of the IPC/J-STD-020D standard for moisture sensitivety testing.

To prevent degradation of temperature cycling capability, care must be taken to prevent solder from flowing into the inner side of the lead frames (inner side of "J" lead in contact with the circuit board).

After soldering, the capacitors should be air cooled to room temperature before further processing. Forced air cooling is not recommended.

Hand soldering should be performed with care due to the difficulty in process control. If performed, care should be taken to avoid contact of the soldering iron to the capacitor body. The iron should be used to heat the solder pad, applying solder between the pad and the lead, until reflow occurs. Once reflow occurs, the iron should be removed immediately. (Preheating is required when hand soldering to avoid thermal shock.)

Profile Feature	SnPb Assembly	Pb-Free Assembly
Preheat/Soak		
Temperature Minimum (T _{Smin})	100°C	150°C
Temperature Maximum (T _{Smax})	150°C	200°C
Time (t_s) from T_{smin} to T_{smax})	60 - 120 seconds	60 - 120 seconds
Ramp-up Rate $(T_L \text{ to } T_P)$	3°C/seconds maximum	3°C/seconds maximum
Liquidous Temperature (T _L)	183°C	217°C
Time Above Liquidous (t _L)	60 - 150 seconds	60 - 150 seconds
Peak Temperature (T _P)	235°C	250°C
Time within 5°C of Maximum Peak Temperature (t,)	20 seconds maximum	10 seconds maximum
Ramp-down Rate (T _P to T _L)	6°C/seconds maximum	6°C/seconds maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum



Note: All temperatures refer to the center of the package, measured on the capacitor body surface that is facing up during assembly reflow.



Table 4 - Performance & Reliability: Test Methods & Conditions


Stress	Reference	Test or Inspection Method
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1.8kg for 60 seconds
Board Flex	JIS-C-6429	Appendix 2, Note: 5.0 mm minimum
		Magnification 50X. Conditions:
Caldarahility	J-STD-002	a) Method B, 4 hours at 155°C, dry heat at 235°C
Solderability	J-51D-002	b) Method B at 215°C category 3
		c) Method D, category 3 at 250°C
Temperature Cycling	JESD22 Method JA-104	1,000 Cycles (-55°C to +125°C), measurement at 24 hours ±4 hours after test conclusion.
Diagod Humaidiku	MII-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion.
Biased Humidity	MIL-STD-202 Method 103	Low Volt Humidity: 1,000 hours 85C°/85%RH and 1.5V. Add 100K ohm resistor. Measurement at 24 hours ±4 hours after test conclusion.
±	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required. Measurement at 24 hours ±4 hours after test conclusion.
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of cycles required – 300, maximum transfer time – 20 seconds, dwell time – 15 minutes. Air – air.
High Temperature Life	MIL-STD-202 Method 108	1,000 hours at 125°C with 1.5X rated voltage applied.
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC, for 1,000 hours.
Vibration	MIL-STD-202 Method 204	5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condition F.
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical – OKEM clean or equivalent.

Storage and Handling

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature – reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. In addition, temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



Construction



Product Marking

Laser marking option is not available on:

- · COG, Ultra-Stable X8R and Y5V dielectric devices
- · EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option
- · KPS Commercial and Automotive grade stacked devices

These capacitors are supplied unmarked only.



Tape & Reel Packaging Information

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration - Embossed Plastic (mm)

EIA Case Size	Tape Size (W)*	Pitch (P ₁)*
01005 - 0402	8	2
0603 - 1210	8	4
1805 - 1808	12	4
≥ 1812	12	8
KPS 1210	12	8
KPS 1812 and 2220	16	12
Array 0612	8	4

^{*}Refer to Figure 1 for W and P_1 carrier tape reference locations.

^{*}Refer to Table 5 for tolerance specifications.



Figure 1 – Embossed (Plastic) Carrier Tape Dimensions




Table 6 - Embossed (Plastic) Carrier Tape Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)											
Tape Size	D ₀	D ₁ Minimum Note 1	E ₁	P ₀	P ₂	R Reference Note 2	S ₁ Minimum Note 3	T Maximum	T ₁ Maximim		
8 mm		1.0 (0.039)				25.0 (0.984)					
12 mm	1.5 +0.10/0.0-0.0 (0.059 +0.004/-0.0)		1.75 ±0.10 (0.069 ±0.004)	4.0 ±0.10 (0.157 ±0.004)	2.0 ±0.05 (0.079 ±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)		
16 mm		(0.059)				(1.181)					
Variable Dimensions — Millimeters (Inches)											
Tape Size	Pitch	B ₁ Maximum Note 4	E ₂ Minimum	F	P ₁	T ₂ Maximum	W Maximum	A ₀ , B ₀	, & K ₀		
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5 ±0.05 (0.138 ±0.002)	4.0 ±0.10 (0.157 ±0.004)	2.5 (0.098)	8.3 (0.327)				
12 mm	Single (4 mm) and Double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5 ±0.05 (0.217 ±0.002)	8.0 ±0.10 (0.315 ±0.004)	4.6 (0.181)	12.3 (0.484)	Note 5			
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5 ±0.05 (0.138 ±0.002)	12.0 ±0.10 (0.157 ±0.004)	4.6 (0.181)	16.3 (0.642)				

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 5).
- 3. If $S_1 < 1.0$ mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).
- 4. B_1 dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by A_{o} , B_{o} and K_{o} shall surround the component with sufficient clearance that:
 - (a) the component does not protrude above the top surface of the carrier tape.
 - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
 - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 2).
 - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 3).
 - (e) for KPS Series product, A_n and B_n are measured on a plane 0.3 mm above the bottom of the pocket.
 - (f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



Packaging Information Performance Notes

- 1. Cover Tape Break Force: 1.0 kg minimum.
- 2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:

Tape Width	Peel Strength			
8 mm	0.1 to 1.0 Newton (10 to 100 gf)			
12 and 16 mm	0.1 to 1.3 Newton (10 to 130 gf)			

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.

3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. *Refer to EIA Standards 556 and 624*.

Figure 2 - Maximum Component Rotation




Figure 3 - Maximum Lateral Movement




Figure 4 - Bending Radius







Figure 5 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.

Table 7 - Reel Dimensions

Metric will govern

Constant Dimensions — Millimeters (Inches)										
Tape Size	A	B Minimum	С	D Minimum						
8 mm	178 ±0.20		13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)						
12 mm	(7.008 ±0.008) or	1.5 (0.059)								
16 mm	330 ±0.20 (13.000 ±0.008)									
Variable Dimensions — Millimeters (Inches)										
Tape Size	N Minimum	W ₁	W ₂ Maximum	W ₃						
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)							
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference						
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)							



Figure 6 - Tape Leader & Trailer Dimensions





Figure 7 - Maximum Camber





KEMET Electronics Corporation Sales Offices

For a complete list of our global sales offices, please visit www.kemet.com/sales.

Disclaimer

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

KEMET:

```
C1210C104MAR2L C2220C105M3R1L C1210C335M3R1L C2220C474MAR1L C1210C335K4R1L
C2220C336M3R2L C2220C106M3R1L C2220C156M3R1L C2220C104K4R1L C1210C475M3R2L
C2220C224M3R1L C2220C474K1R1L C2220C475M3R2L C1210C224K5R1L C2220C225K3R1L
C1210C335M3R2L C2220C475M3R1L C2220C474K5R1L C1210C106M4R2L C1210C106M8R2L
C1210C474M3R1L C1210C224M4R2L C1210C104K5R1L C2220C474M1R1L C2220C224M4R2L
C2220C156M4R1L C1210C105K3R1L C1210C104KAR1L C1210C335M4R2L C2220C104K1R1L
C2220C475K5R1L C2220C224MAR2L C2220C335M5R2L C2220C335K4R1L C1210C105K1R1L
C1210C104M4R2L C1210C225M3R1L C2220C226M4R2L C1210C225M4R1L C1210C104M8R1L
C1210C474M5R2L C1210C475M8R1L C1210C106M5R2L C2220C474M4R2L C1210C475M8R2L
C2220C225M5R1L C2220C105K5R1L C1210C226K8R1L C1210C475K3R1L C1210C225M1R2L
C2220C226K3R1L C1210C105M3R1L C2220C474M3R2L C1210C225K3R1L C2220C475M5R1L
C2220C106M4R1L C2220C104M1R2L C1210C156M8R1L C2220C225K4R1L C2220C225M5R2L
C1210C105M3R2L C2220C226M4R1L C2220C224K3R1L C2220C335M4R1L C2220C335M4R2L
C2220C105M4R2L C1210C335K3R1L C2220C474M4R1L C1210C104K3R1L C1210C474M1R1L
C1210C226M3R2L C1210C104M8R2L C2220C335M3R1L C2220C474M1R2L C1210C336M8R2L
C1210C224M3R2L C1210C225M4R2L C1210C475K8R1L C2220C474MAR2L C1210C106M8R1L
C1210C105M5R1L C2220C105KAR1L C1210C335M5R1L C2220C225M1R2L C2220C335K1R1L
C1210C225K5R1L C2220C225M3R2L C1210C476M8R2L C2220C105M5R1L C1210C335M4R1L
C2220C105K1R1L C2220C226K4R1L C2220C476M4R2L C2220C224M5R1L C1210C474M5R1L
C2220C224K5R1L C1210C105M8R1L C1210C105M8R2L C1210C224K8R1L C2220C106M3R2L
```